

Mipa 1K-Klarlack C 10

gb 7/1010

page 1 / 1

Professional Coating Systems

Product Information

1K-Acrylic clear coat designed to give good protection to ultra-violet light. Recommended as overcoat for two coat paintings. Good resistance to weathering as well as good performance against petroleum by temporary exposure. Consumption: 6 - 8 m²/l.

Colour shade	colourless				
Mixing ratio					
Hardener					
Thinners					
Spraying viscosity 20°C	ready for spraying				
Application	spraying pres	sure	sprayir	ng nozzle	spraying operations
Spray gun - Air /Flowjar	4 - 5 bar	-	1.	5 mm	2 - 3
Airless / Airmix	120 - 150 bar		0.2	28 mm	2 - 3
Pot life					
Coat thickness / dry film	30 - 40 μm				
Curing time / Flash off time	5 - 10 min. between the spraying operations				
Dry	recoat time	dust dry		set to touc	h full hardness
Object temp. 20°C		30 - 40 min.		4 h	24 h
Object temp. 60°C		10 - 15 min.		30 - 60 n	nin. after cooling
Special Recommandations	We advise against using this product for "clear-over-base" applications on water-borne base paints.				

Storage stability: at least 3 years if stored in tightly closed original containers.

All products should be disposed of in relation to the regulations of the environmental health authorities. Protect your Environment!

This data sheet is for information purpose only! To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacture of our products. However the data is not binding and without warranty. Please follow recommendations stated on the relevant safety data sheet and precautions stated on the product label. We reserve our right to make additions, deletions, or modifications to the information at any time without prior notification.

MIPA AG · D-84051 Essenbach · Tel. 08703/9220 · Telefax 08703/922100