

Update date: 09.2023

# TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

## **Matt 2:1**

Matt 2:1 ACRYLIC CLEARCOAT

#### **PRODUCTS**

Matt 2:1 Acrylic Clear Coat - Clear coat with matt effect.

Hardener 1:2 for Matt 2:1 Acrylic Clear Coat.

Thinner for acrylic systems.

### **PRODUCT DESCRIPTION**

High-quality matt acrylic clear coat with a special effect. Intended for specialized repairs of car body parts that require a matt finish. It allows to obtain an evenly matt surface as well as a strong and durable finish.

- Excellent look of the coat.
- Very good flow and levelling.
- Durable coating.

Matt 2:1 Clear Coat can be mixed with Inter Troton Crystal and Zircon clear coats, as well as with Multi Füller MS 2:1.

Different degrees of matt is obtained depending on mixture ratios.



**COLOUR:** milky

GLASS GRADE: full matt

## **VOLATILE ORGANIC COMPOUNDS**

VOC for the mixture = 593,7 [g/I]

This product meets the EU directive (2004/42/EC/II B) that sets the VOC value for its category (e), at 840 g/l.

## **SURFACE PREPARATION**

Acrylic Clear Coats can be applied over:

- Base Coats.
- Old finishes in good condition after matting and degreasing.

For matting we recommend the following:

- grey abrasive fabric with a polishing compound,
- sanding paper with gradation of 600÷800 (wet sanding),

- sanding paper with gradation of 360÷400 (machine sanding).

APPLICATION PROCESS					
USE		NUMBER OF LAYERS			

APPLICATION PROCESS				
	USE		NUMBER OF LAYERS	
	Product is specially designed for repairs to exterior paint, that require matt finish.		2 full layers, total dry film thickness of approx. 50-60 μm.  RP gun parameters:	
	MIXING RATIO by vol	ume	Nozzle: 1.3÷1.4mm; Pressure of input: 2.0÷2.2 bars.	
	Clear coat 2 parts		HVLP gun parameters:	
	Hardener 1 part		Nozzle: 1.3÷1.4mm; Pressure of input: 2.0 bars.	
	Thinner 10%		Note: follow the gun producer's recommendations.	
	SPRAYING VISCOSITY		HARDENING TIME	
s	16÷18 seconds at 20°C.		Dust dry: 30 minutes at 20°C Touch dry: 24 hours at 20°C Temperature below 20°C significantly increases the hardening time.	
	POT LIFE		EVAPORATION TIME	
	Approx. 7 hours at 20°C.	<u> </u>	Between layers: 10÷15 minutes	



Update date: 09.2023

### **DEGREES OF THE MATTING EFFECT**

Coatings	Mixture of Clear Coat (Mix before adding Hardener)		Hardener	Thinner 10%
Matting Effect	Matt 2:1	IT Crystal or Zircon or MF MS 2:1	Matt 1:2	for acrylic systems
FULL MAT	100 ml		50 ml	15 ml
EGG SHELL	90 ml	10 ml	50 ml	15 ml
SEMI GLOSS	75 ml	25 ml	50 ml	15 ml
FULL GLOSS		100 ml	50 ml	15 ml

#### **PRODUCT EFFICIENCY**

1 liter of mixture is enough to cover 8÷9 m² with a dry layer with thickness of 50 μm.

### POLISHING AND REMOVING IMPURITY INCLUSIONS

Note: Do not polish!

#### **GENERAL NOTES**

- Do not exceed recommended doses of the hardener!
- The best repair results can be achieved at room temperature. The temperature in the body shop and the temperature of the
  product should be similar.
- When working with 2K products, it is recommended to use personal protection equipment. Protect the eyes and respiratory system.
- The rooms should be well ventilated.
- Clean the guns and equipment immediately after use.
- Produkt należy dobrze wymieszać.
- Nie nakładać grubych warstw.
- Różne techniki aplikacji prowadzą do różnych stopni połysku.

Caution: To maintain safety, always follow the instructions given in the MSDS for the products.

### **STORAGE**

Store the product between 15 to 25°C in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight.

#### Note:

- 1. After each use the container with product should be immediately closed.
- 2. Protect the hardener from frost and dampness!

WARRANTY PERIOD	
Matt 2:1 Acrylic Clear Coat.	<ul> <li>12 months from the date of manufacture.</li> </ul>
Hardener 1:2 for Matt 2:1 Acrylic Clear Coat.	<ul> <li>12 months from the date of manufacture.</li> </ul>
Thinner for acrylic systems.	<ul> <li>12 months from the date of manufacture.</li> </ul>

PRODUCTS	Art. No.
Matt 2:1 Acrylic Clear Coat	6301 (11)
Hardener 1:2 for Matt 2:1 Acrylic Clear Coat	6300 (0.51)
Thinner for acrylic systems	

## **LIMITATION OF LIABILITY**

The information contained in the TDS is up-to-date and correct on the day the information is released.

Because TROTON can not control or predict the conditions under which a product will be used, each user should review information in the specific context of the intended usage. To the maximum extent permitted by applicable law, TROTON shall not be liable for damages of any kind arising from the use or reliance on information contained in this TDS.

Given the variety of factors that can affect the usage and application of the TROTON product, some of which are only within the user's knowledge and control range, it is essential that the user evaluate the TROTON product to determine if the product is fit for a particular purpose and whether the product is suitable for the user's usage.

Under no circumstances shall TROTON be liable to the user or any third party for any indirect, derivative, incidental, special or punitive damages, including loss of profits resulting from the use of products manufactured by TROTON and / or TROTON's services.

All information are based upon the precise laboratory studies and many years of experience. The good market position does not release us from the constant supervision of our products quality. However, we are not responsible for the final effects of the improper storage or application of our products, as well as for work inconsistent with the good craft practice.

TROTON Sp. z o.o. Ząbrowo, Poland.