# **TECHNICAL INFORMATION**

FOR PROFESSIONAL USE ONLY

addsTROTON SPRAY ZINC – ALU PRIMER



### PRODUCT DESCRIPTION

Zinc – alu primer has excellent anti-corrosive properties to repair zinc-plated part and surfaces. Product is suitable also for others blank metals, partly applicable for aluminium . Can be use for zincplated parts and surfaces which have been damaged by welding, grinding, drilling, transporting etc. and need to be repaired or coloured. Also suitable as an excellent anti-corrosive agent for metal surfaces and blank iron metals.

| PHYSICAL AND CHEMICAL PROPERTIES |                  |   |
|----------------------------------|------------------|---|
| •                                | Capacity:        | 400 ml                                      |
| •                                | Base:            | phenol resin                                |
| •                                | Degree of gloss: | silver – metalic                            |
| •                                | Corrosion:       | resistant                                   |
| •                                | Heat resistant:  | up to 300 <sup>0</sup> C                    |
| •                                | Coatable:        | with air-drying acrylic or synthetic paints |
| Drying time*:                    |                  |   |
| •                                | Dust-dry         | after approx.15 minutes                     |
| •                                | Dry to touch     | after approx. 60 minutes                    |
| •                                | Dry              | after approx 12 hours                       |

\* drying time depends on the temperature, humidity and thickness of the coating.



## VOC CONTENT

VOC = 815 [g/l].

The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat..B/5) at the level of 840[g/I] for the ready product.

USAGE

- The ground must be clean, dry and free of rust and grease.
- Shake before using for 2 minutes and try it on cardboard.
- Spray and cover with several layers.
- During lacquering hold aerosol in 25÷30 cm distance from the surface.
- After drying (approx. 12-24 hrs.) the area can be primed and painted, if necessary.
- Can be coated with air-drying acrylic and synthetic resin paints.

#### STORAGE

Store the product components in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight.

#### **EXPIRY DATE**

5 years from production date.

All information are based upon the precise laboratory studies and many years of experience. The good market position does not release us from the constant supervision of our products quality. However we are not responsible for the final effects of the improper storage or application of our products, as well as for work inconsistent with the good craft practice.

TROTON Sp. z o.o. Ząbrowo, Poland